

**ACMI #2001**  
**NON-POROUS**  
**STAMP PAD**  
**STENCIL**

Description: ACMI #2001 was formulated for marking glass, plastics, metals, film, foil and other nonporous substrates, as well as porous substrates. This ink has excellent resistance to petroleum solvents and trichlorethylene.  
Meets: CID A-A-208B Types I & IV  
Formerly: TT-I-1795a

**SPECIFICATIONS:**

Applications: Cloth covered felt stamp pad, with pad life relative to dry time  
Stencil roller with pad or brush

Viscosity: 150 cps

Specific Gravity: 1.00-1.20

Weight per Gallon: 8.33 - 10.0 lbs.

Flashpoint: 66° F. - 70° F.

Dry time: 120-150 seconds

Variations in temperature and humidity may affect dry time.

Shelf Life & Storage: 24 months, stored at normal room temperature. Ink should be capped tightly after each use.

Chemical Base: Solvent

Colorant Base: Pigment

**RECONDITIONER:** #2001 Reconditioner

**COLORS:** Black, Gray, Red, Pink, White, Blue, Gold, Yellow, Orange, Green, Brown, Maroon, Magenta, Violet

**AVAILABILITY:** Pints, Quarts and Gallons

Smaller sizes available on request

STATEMENT OF LIABILITY

Neither the manufacturer nor the seller shall be liable for any injury, loss or damage arising out of the use of this product. The only obligations of the manufacturer or the seller shall be to replace any quantity of this product found to be defective or, at the option of the seller or manufacturer, to refund the purchase price. The purchaser or user of this product should, before use of the product, determine whether it is suitable for that use. The user assumes all risk and liability in connection with that use.

THE FOREGOING IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED

***American Coding and Marking Ink Co. Inc.***

1220 North Avenue, Plainfield, NJ 07062

**Phone:** 908-756-0373 **Fax:** 908-756-0570 **Web Site:** [www.americancoding.com](http://www.americancoding.com)