

ACMI #6821
High Temperature
RESISTANT
INK

Description:

ACMI #6821 was formulated for brush or air-spray stenciling onto metals, glass and ceramics. This ink is resistant to 600° F. when properly cured.

SPECIFICATIONS:

Applications: Brush or air-spray stenciling onto metals, glass and ceramic

Curing Temperature: 300°- 500° F. for 1 hour

Resistant Temperature: 600° F.

Viscosity: 420 cps

Specific Gravity: 1.10

Weight per Gallon: 9.17 lbs

Flashpoint: 89° F.

Dry time: 2 minutes

Variations in temperature and humidity may affect dry time.

Shelf Life & Storage: Use within 1 year is recommended. Ink should be stored at normal room temperature and capped tightly after each use.

Chemical Base: Solvent

Colorant Base: Pigment

RECONDITIONER: #6821 Reconditioner

COLORS: Black, White, Blue, Silver, Brown, Gray, Red, Orange, Yellow, Green

AVAILABILITY: Pints, Quarts and Gallons, Smaller sizes available on request

STATEMENT OF LIABILITY

Neither the manufacturer nor the seller shall be liable for any injury, loss or damage arising out of the use of this product. The only obligations of the manufacturer or the seller shall be to replace any quantity of this product found to be defective or, at the option of the seller or manufacturer, to refund the purchase price. The purchaser or user of this product should, before use of the product, determine whether it is suitable for that use. The user assumes all risk and liability in connection with that use.

THE FOREGOING IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED

American Coding and Marking Ink Co. Inc.

1220 North Avenue, Plainfield, NJ 07062

Phone: 908-756-0373 **Fax:** 908-756-0570 **Web Site:** www.americancoding.com